



Grade Data Sheet

Durinox™ F18MS

Durinox F18MS is a stabilised chromium-molybdenum ferritic stainless steel, combining very good corrosion resistance with good formability and weldability. Its excellent corrosion resistance enables it to replace grade 316 in many applications; domestic hot water cylinders are its largest field of application. Like all ferritic steels it is readily attracted to a magnet.

Durinox F18MS is most commonly available in sheet or coil up to about 2mm thick.

Corrosion Resistance

Durinox F18MS has good resistance in a wide variety of corrosive media. It attains its maximum corrosion resistance when in the highly polished or buffed condition.

The resistance of grade F18MS to pitting and crevice corrosion in chloride environments is similar or superior to that of grade 316. Its PRE value of about 25 is at least as high as that of 316. Chloride stress corrosion cracking (SCC) resistance of Durinox F18MS is very high, as it is for all ferritic grades.

The resistance of Durinox F18MS to acids is generally lower than that of 316, but performance varies for different acids, and these should be considered on a case by case basis.

Heat Resistance

Durinox F18MS resists oxidation in intermittent service up to 920°C and to 870°C in continuous service but it may become brittle at room temperature after prolonged heating in the 400 – 500°C range. This effect can be corrected by subsequent annealing.

Heat Treatment Annealing

Heat to approximately 925°C, hold for only a few minutes and then water quench or quickly air cool. Slow cooling from 500-400°C will cause embrittlement.

Durinox F18MS is not hardenable by thermal treatment.

Welding

Welding of Durinox F18MS can be readily carried out by all the common electric processes. As F18MS has very low carbon and nitrogen contents and is stabilised by additions of titanium and / or niobium it has good resistance to sensitisation and hence intergranular corrosion. Like most ferritic grades it is subject to significant grain growth in the heat affected zones of welds. Heat input should therefore be kept to a minimum, and welding of thicknesses over 2mm become more difficult. Gas shielding of the arc, weld metal and back side of the weld is important to minimise air contact. Use Grade 316L (or 316LSi) filler rod, depending upon application. AS 1554.6 pre-qualifies welding (listed as Grade 444) with Grade 316L filler rods and electrodes.

Machining

F18MS is easier to machine than the standard austenitic grades such as 316, but the grade is not commonly available as a bar.

Fabrication

Durinox F18MS has a higher yield strength, higher tensile strength and lower work hardening rate compared to 316. Some operations will therefore be easier and some will require a little more force. The lower ductility of F18MS restricts some very severe operations. It has quite good deep drawing capability; close to that of 316, but it has limited ability to stretch form. As these two processes are often combined in a single forming operation some changes to settings or tooling compared to the austenitic grades may be needed.

If very severe cold working is required it may be necessary to carry out an intermediate anneal.

Typical Applications

Hot water cylinders, heat exchanger tubing, chemical process equipment, architectural panels.

Specified Properties

The composition and mechanical properties are specified for flat rolled product (plate, sheet and coil) in ASTM A240/A240M, for grade 444 (UNS S44400). Durinox F18MS is fully compliant with this specification. Similar but not necessarily identical properties are specified for other products in their respective specifications.

Chemical Composition (%)

| Grade | C | Mn | Si | P | S | Cr | Mo | Ni | N | Ti+Nb |
|---------------|-------|------|------|-------|-------|------|------|------|-------|-------------|
| Durinox F18MS | - | - | - | - | - | 17.5 | 1.75 | - | - | 0.20+4(C+N) |
| | 0.025 | 1.00 | 1.00 | 0.040 | 0.030 | 19.5 | 2.50 | 1.00 | 0.035 | 0.80 |

Mechanical Properties

| Grade | Tensile Strength (MPa) min | Yield Strength 0.2% Proof (MPa) min | Elongation (% in 50mm) min | Hardness | | Cold Bend Transverse direction Bend radius = 1T |
|---------------|----------------------------|-------------------------------------|----------------------------|-----------------------|------------------|---|
| | | | | Rockwell B (HR B) max | Brinell (HB) max | |
| Durinox F18MS | 415 | 275 | 20 | 96 | 217 | 180° |

Physical Properties

(typical values in the annealed condition)

| Grade | Density (kg/m ³) | Elastic Modulus (GPa) | Mean Coefficient of Thermal Expansion | | Thermal Conductivity at 100°C (W/m.K) | Specific Heat 0-100°C (J/kg.K) | Electrical Resistivity (nΩ.m) |
|---------------|------------------------------|-----------------------|---------------------------------------|-------------------|---------------------------------------|--------------------------------|-------------------------------|
| | | | 0-100°C (µm/m/°C) | 0-400°C (µm/m/°C) | | | |
| Durinox F18MS | 7700 | 200 | 11.0 | 11.5 | 26.8 | 427 | 620 |

Grade Specification Comparison

| Grade | UNS No | Euronorm | | Swedish SS | Japanese JIS |
|---------------|--------|----------|--------------|------------|--------------|
| | | No | Name | | |
| Durinox F18MS | S44400 | 1.4521 | X2CrMoTi18-2 | 2326 | SUS 444 |

These comparisons are approximate only. The list is intended as a comparison of functionally similar materials **not** as a schedule of contractual equivalents. If exact equivalents are needed original specifications must be consulted.

Possible Alternative Grades

| Grade | Why it might be chosen instead of Durinox F18MS |
|-------|--|
| 316 | Need the increased weldability, especially in heavy sections, or better stretch formability of 316. 316 is also available in sections above the 2 to 3mm upper limit for Durinox F18MS, and a wider range of products generally. |
| 2304 | 2304 has better weldability in heavy sections, and higher strength that may allow down-gauging. |
| F20S | Durinox F20S could be used if the corrosion resistance of F18MS was not needed. Another low cost ferritic steel. |

Limitation of Liability

The information contained in this datasheet is not an exhaustive statement of all relevant information. It is a general guide for customers to the products and services available from Atlas Steels and no representation is made or warranty given in relation to this document or the products or processes it describes.